



WOLLE

WOLLE P2100

Semi-rigid thermal insulation fibre boards, higher density — 10 cm thickness, 5.856 m² pack

Semi-rigid thermal insulation fibre boards, Wolle higher-performance variant: the same recycled PET fibre, with higher mass per area and better thermal conductivity. The main layer in the System 10 Basic +, Medium + and Premium + packages.

TECHNICAL CHARACTERISTICS

Material	Thermal insulation fibre from recycled PET, free of binders, formaldehyde or phenol	
Thickness	100 mm	
Board dimensions	1200 × 610 × 100 mm	
Mass per unit area	2100 g/m²	
Pack contents	8 boards — 5.856 m²	
Thermal conductivity, λ_{10}	0.035 W/mK	SR EN 12667:2002
Thermal resistance of the layer, R	2.86 m²K/W	SR EN 12667:2002
Reaction to fire	C-s2,d0 — zero flaming droplets	EN 13501-1
German classification	B1	DIN 4102
Moisture behaviour	Fully hydrophobic — does not absorb moisture and releases it quickly	
Acoustic behaviour	Sound-absorbing fibre — reduces airborne noise	
Long-term stability	No settling — constant performance over time, including in sloped cavities	

FIELDS OF USE

Attics and roofs (main layer between rafters) — System 10 Basic +, Medium + and Premium + packages; interior walls, floors between storeys, ventilated facades.

PACKAGING AND STORAGE

Packs stored in covered spaces, protected from moisture and direct sunlight.

INSTALLATION

Installed between rafters, as whole boards or cut to the width of the gap, without compression. In assemblies that also include a 5 cm layer (P800), this is installed first. Boards are cut with the Wolle Sword knife.

S.C. ISO FLECT INSULATION S.R.L.

CIF RO30340616 · Reg. com. J2012000359286
Şos. Caragea Vodă nr. 89A, Domneşti, sat Țegheș, jud. Ilfov, Romania

Warehouse and deliveries

ELI Park 3, secțiunea S10, Str. Speranței 101, Buftea, Ilfov, Romania
+40 21 780 7585 · WhatsApp +40 790 644 051 · contact@isoflect.ro

The declared values come from the Isoflect Insulation product documentation and the related test reports. They refer to the product, not to the assembly in which it is installed; system performance is established through a hygrothermal calculation for each individual case. The manufacturer reserves the right to change specifications without prior notice — always check the revision in force. Revision 4 · 13.09.2026