



WOLLE

WOLLE P800

Semi-rigid thermal insulation fibre boards — 5 cm thickness, 11.712 m² pack

Semi-rigid thermal insulation fibre boards made from recycled PET, free of binders, formaldehyde and phenol. The infill layer in the 15 and 25 cm System 10 assemblies.

TECHNICAL CHARACTERISTICS

Material	Thermal insulation fibre from recycled PET, free of binders, formaldehyde or phenol	
Thickness	50 mm	
Board dimensions	1200 × 610 × 50 mm	
Mass per unit area	800 g/m²	
Pack contents	16 boards — 11.712 m²	
Thermal conductivity, λ_{10}	0.038 W/mK	SR EN 12667:2002
Thermal resistance of the layer, R	1.32 m²K/W	SR EN 12667:2002
Reaction to fire	C-s2,d0 — zero flaming droplets	EN 13501-1
German classification	B1	DIN 4102
Moisture behaviour	Fully hydrophobic — does not absorb moisture and releases it quickly	
Acoustic behaviour	Sound-absorbing fibre — reduces airborne noise	
Long-term stability	No settling — thickness and performance remain constant	

FIELDS OF USE

Attics and roofs (infill layer between rafters), interior walls, partition walls, floors between storeys, ventilated facades.

PACKAGING AND STORAGE

Packs stored in covered spaces, protected from moisture and direct sunlight.

INSTALLATION

In any assembly that also includes a 5 cm layer — i.e. at 15 and 25 cm — the 5 cm layer is ALWAYS installed FIRST, before the 10 cm layer: the first layer installed self-fixes, whereas a 5 cm layer installed last would need to be anchored. Boards are cut with the Wolle Sword knife. No conventional protective equipment is required — the fibre is not irritant.

S.C. ISO FLECT INSULATION S.R.L.

CIF RO30340616 · Reg. com. J2012000359286

Șos. Caragea Vodă nr. 89A, Domnești, sat Țegheș, jud. Ilfov, Romania

Warehouse and deliveries

ELI Park 3, secțiunea S10, Str. Speranței 101, Buftea, Ilfov, Romania

+40 21 780 7585 · WhatsApp +40 790 644 051 · contact@isoflect.ro

The declared values come from the Isoflect Insulation product documentation and the related test reports. They refer to the product, not to the assembly in which it is installed; system performance is established through a hygrothermal calculation for each individual case. The manufacturer reserves the right to change specifications without prior notice — always check the revision in force. Revision 4 · 13.09.2026